

Data Sheet

TH208 Nickel Aluminum

DESCRIPTION

TH208 is a nickel aluminum molybdenum cored wire specifically designed for arc spraying. The coatings that are produced, offer superb wear resistance and good corrosion resistance.

TYPICAL DEPOSIT CHARACTERISTICS:

Bond Strength 7500 psiTypical Hardness HRB 75-85

• Deposit Rate 18 lbs./hr./150-200 Amps

• Deposit Efficiency 75%

• Wire Coverage 2 sq. ft./lbs. @ 12 mils

Surface Texture VariableMachinability Good

SURFACE PREPARATION:

Surface should be clean, white metal, with no oxides (rust), dirt, grease, or oil on the surface to be coated. NOTE: It is best not to handle surfaces after cleaning. Recommended method of preparation is, to grit blast with 24 mesh aluminum oxide, rough grind, or rough machine in a lathe. *Thermion recommends a 3.5 mil minimum anchor tooth profile.

Applications:

- Machine Element Repair
- Dimensional Restoration
- Wear Resistance

NOMINAL CHEMICAL COMPOSITION (wt. %):

Al	Мо	Ni
5.5	5.0	Bal

RECOMMENDED SPRAY PARAMETERS:

Diameter	Air Pressure	Voltage	Amperage	Standoff
I/I6" (I.6mm)	80-100 psi	28-32	100-300	4-7" (10-17cm)

Parameters are typical and may vary depending on equipment used.

STANDARD SIZES & PACKAGING:

Diameter Packaging

I/I6 (I.6mm) 25#